

Dow Corning® OE-6250 Optical Encapsulant

FEATURES & BENEFITS

- No cure by-product
- Solventless
- Low viscosity
- Low moisture absorption
- Low temperature cure
- High transparency
- Excellent thermal stability
- Excellent stress reduction
- Excellent dielectric properties

COMPOSITION

- Polydimethylsiloxane

Two-part, solventless, high purity, gel encapsulant for LED.

APPLICATIONS

- *Dow Corning®* OE-6250 Optical Encapsulant is designed to seal and protect LEDs.

TYPICAL PROPERTIES

Specification Writers: These values are not intended for use in preparing specifications. Please contact your local Dow Corning sales office or your Global Dow Corning Connection before writing specifications on this product.

| Property | Unit | Result |
|---|-----------|-----------|
| One or Two-Part | - | Two |
| Mix Ratio | - | 1:1 |
| Color | - | Colorless |
| Viscosity (Part A) | cP | 470 |
| | Pa-sec | 0.5 |
| Viscosity (Part B) | cP | 460 |
| | Pa-sec | 0.5 |
| Viscosity (Mixed) | cP | 470 |
| | Pa-sec | 0.5 |
| Working Time at 25 °C (Pot Life – hours) | hours | 0.8 |
| Specific Gravity (Uncured Part A or Base) | - | 0.98 |
| Specific Gravity (Uncured Part B or Catalyst) | - | 0.98 |
| Heat Cure Time at 80 °C | minutes | 60 |
| Penetration | 1/10 mm | 45 |
| Impurity (Na+) | Ppm | 0.1 |
| Impurity (K+) | Ppm | 0.2 |
| Impurity (Cl-) | Ppm | 1 |
| Volume Resistivity | ohm*cm | 5E+13 |
| Dielectric Strength | volts/mil | 380 |
| | kV/mm | 15 |
| Dielectric Constant at 1 MHz | - | 3.3 |
| Dissipation Factor at 1 MHz | - | 9E-04 |
| Refractive Index | - | 1.41 |
| Transparency at 450 nm, 1 mm thick | % | 99.7 |

DESCRIPTION

Dow Corning® brand silicone LED (light emitting diode) encapsulants are designed to meet the challenging needs of the LED market, including high adhesion, high purity, moisture resistance, thermal stability and optical transmittance. Silicone materials can absorb stresses caused by thermal cycling inside the package, protecting the chip and the bonding wires. And with the electronics industry quickly moving toward lead-free processing, silicone encapsulants, with their

demonstrated, excellent stability at reflow temperatures, are a natural fit for LED applications.

APPLICATION METHODS

- Compatible with commercially available equipment and industry standard processes

PREPARING SURFACES

Surfaces should be clean and dry. Recommended cleaning methods include *Dow Corning®* brand OS Fluids,

naphtha, mineral spirits, methyl ethyl ketone (MEK) or other suitable solvent. Rougher surfaces tend to promote adhesion of silicones to other surfaces.

PROCESSING/CURING

These products are also compatible with commercially available equipment and industry standard processes. These materials can be dispensed or molded depending on the product and application. *Dow Corning* OS Fluids are recommended to clean cured or uncured silicone residue from application equipment.

ADHESION

Dow Corning LED materials are specially designed for adhesion to commonly used LED substrates. Surface treatments such as chemical etching or plasma treatment may provide a reactive surface and improve adhesion to these types of substrates. In general, increasing the cure temperature and/or cure time will improve the ultimate adhesion.

USEFUL TEMPERATURE RANGES

For most uses, silicone encapsulants and resins should be operational over a temperature range of -45 to 200°C (-49 to 392°F) for long periods of time. However, at both the low- and high-temperature ends of the spectrum, behavior of the materials and performance in particular applications can become more complex and require additional considerations. For low-temperature performance, thermal cycling to conditions such as -55°C (-67°F) may be possible, but performance should be verified for your parts or assemblies. Factors that may influence performance are configuration and stress sensitivity of components, cooling rates and hold times, and prior temperature history. At the high-temperature end, the durability of the cured silicone elastomer is time and temperature dependent. As expected, the higher the temperature, the shorter the time the material will remain useable.

COMPATIBILITY

Certain materials, chemicals, curing agents and plasticizers can inhibit the cure of addition cure adhesives. Most notable of these include: organotin and other organometallic compounds, Silicone rubber containing organotin catalyst, sulfur, polysulfides, polysulfones or other sulfur containing materials, unsaturated hydrocarbon plasticizers, and some solder flux residues. If a substrate or material is questionable with respect to potentially causing inhibition of cure, it is recommended that a small scale compatibility test be run to ascertain suitability in a given application. The presence of liquid or uncured product at the interface between the questionable substrate and the cured gel indicates incompatibility and inhibition of cure.

HANDLING

**PRECAUTIONS
PRODUCT SAFETY
INFORMATION REQUIRED
FOR SAFE USE IS NOT
INCLUDED IN THIS
DOCUMENT. BEFORE
HANDLING, READ PRODUCT
AND MATERIAL SAFETY DATA
SHEETS AND CONTAINER
LABELS FOR SAFE USE,
PHYSICAL AND HEALTH
HAZARD INFORMATION. THE
MATERIAL SAFETY DATA
SHEET IS AVAILABLE ON THE
DOW CORNING WEB SITE AT
DOW CORNING.COM, OR
FROM YOUR DOW CORNING
SALES APPLICATION
ENGINEER, OR DISTRIBUTOR,
OR BY CALLING DOW
CORNING CUSTOMER
SERVICE.**

USABLE LIFE AND STORAGE

Shelf life is indicated by the "Use Before" date found on the product label. Dow Corning two-part products should be stored at or below 25°C (77°F). Containers should be kept tightly closed at all times to extend

shelf life. Check the product label for specific storage conditions.

LIMITATIONS

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

HEALTH AND ENVIRONMENTAL INFORMATION

To support Customers in their product safety needs, Dow Corning has an extensive Product Stewardship organization and a team of Product Safety and Regulatory Compliance (PS&RC) specialists available in each area.

For further information, please see our Website, dowcorning.com or consult your local Dow Corning representative.

LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow Corning's sole warranty is that our products will meet the sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

**DOW CORNING SPECIFICALLY
DISCLAIMS ANY OTHER
EXPRESS OR IMPLIED
WARRANTY OF FITNESS FOR A**

**PARTICULAR PURPOSE OR
MERCHANTABILITY.**

**DOW CORNING DISCLAIMS
LIABILITY FOR ANY
INCIDENTAL OR
CONSEQUENTIAL DAMAGES.**

**HOW CAN WE HELP YOU
TODAY?**

Tell us about your performance,
design and manufacturing challenges.
Let us put our silicon-based materials
expertise, application knowledge and
processing experience to work for
you.

For more information about our
materials and capabilities, visit
dowcorning.com.

To discuss how we could work
together to meet your specific needs,
email **electronics@dowcorning.com**
or go to **dowcorning.com/contactus**
for a contact close to your location.
Dow Corning has customer service
teams, science and technology
centers, application support teams,
sales offices and manufacturing sites
around the globe.

We help you invent the future.™

dowcorning.com