

# ***Dow Corning*<sup>®</sup> OE-6550 Optical Encapsulant**

## **FEATURES & BENEFITS**

- Two Part, 1:1 mix ratio
- High transmittance
- Medium viscosity
- Medium hardness
- High refractive index
- Excellent optical properties
- Long pot life

## **COMPOSITION**

- Methylphenyl Siloxane

Two part, 1:1 mix ratio, medium viscosity, high RI, transparent silicone elastomer

## **APPLICATIONS**

*Dow Corning*<sup>®</sup> OE-6550 Optical Encapsulant is designed for LED encapsulation.

## **TYPICAL PROPERTIES**

Specification Writers: These values are not intended for use in preparing specifications. Please contact your local Dow Corning sales office or your Global Dow Corning Connection before writing specifications on this product.

<b>Property</b>	<b>Unit</b>	<b>Result</b>
One or Two-Part	-	Two
Color	-	Colorless
Viscosity (Part A)	cP	23,600
	Pa-sec	23.6
Viscosity (Part B)	cP	920
	Pa-sec	1
Viscosity (Mixed)	cP	3,800
	Pa-sec	3.8
Mix Ratio	-	1 to 1
Durometer Shore A	-	55
Specific Gravity (Cured)	-	1.15
Heat Cure Time at 150 °C	minutes	60
Tensile Strength	psi	190
	MPa	1.3
	kg/cm2	13
Elongation	%	75
Refractive Index	-	1.54
Transparency at 450 nm, 1 mm thick	%	100
Linear CTE (by TMA)	ppm/°C	210
Youngs Modulus	psi	740
	Mpa	5.1
	kg/cm2	52
Dielectric Strength	volts/mil	900
	kV/mm	35
Dielectric Constant at 1 MHz	-	3.3
Volume Resistivity	ohm*cm	9E+15
Unprimed Adhesion - Die Shear (Al)	psi	250
	MPa	1.7
	kg/cm2	170
Impurity (Na+)	ppm	0.1
Impurity (K+)	ppm	0.2
Impurity (Cl-)	ppm	1
Dissipation Factor at 1 MHz	-	9E-03

## DESCRIPTION

*Dow Corning*<sup>®</sup> brand silicone LED (light emitting diode) encapsulants are designed to meet the challenging needs of the LED market, including high adhesion, high purity, moisture resistance, thermal stability and optical transmittance. Silicone materials can absorb stresses caused by thermal cycling inside the package, protecting the chip and the bonding wires. With the electronics industry quickly moving toward lead-free processing, silicone encapsulants, with their demonstrated, excellent stability at reflow temperatures, are a natural fit for LED applications.

## APPLICATION METHODS

- Compatible with commercially available equipment and industry standard processes

## PROCESSING/CURING

These products are also compatible with commercially available equipment and industry standard processes. These materials can be dispensed or molded depending on the product and application. *Dow Corning*<sup>®</sup> brand OS Fluids are recommended to clean cured or uncured silicone residue from application equipment.

## ADHESION

*Dow Corning* LED materials are specially designed for adhesion to commonly used LED substrates. Surface treatments such as chemical etching or plasma treatment may provide a reactive surface and improve adhesion to these types of substrates. In general, increasing the cure temperature and/or cure time will improve the ultimate adhesion.

## USEFUL TEMPERATURE RANGES

For most uses, silicone encapsulants and resins should be operational over a temperature range of -45 to 200 °C (-49 to 392 °F) for long periods of time. However, at both the low- and high-temperature ends of the spectrum, behavior of the materials

and performance in particular applications can become more complex and require additional considerations. For low-temperature performance, thermal cycling to conditions such as -55 °C (-67 °F) may be possible, but performance should be verified for your parts or assemblies. Factors that may influence performance are configuration and stress sensitivity of components, cooling rates and hold times, and prior temperature history. At the high-temperature end, the durability of the cured silicone elastomer is time and temperature dependent. As expected, the higher the temperature, the shorter the time the material will remain useable.

## COMPATIBILITY

Certain materials, chemicals, curing agents and plasticizers can inhibit the cure of addition cure adhesives. Most notable of these include: organotin and other organometallic compounds, silicone rubber containing organotin catalyst, sulfur, polysulfides, polysulfones or other sulfur containing materials, unsaturated hydrocarbon plasticizers, and some solder flux residues. If a substrate or material is questionable with respect to potentially causing inhibition of cure, it is recommended that a small scale compatibility test be run to ascertain suitability in a given application. The presence of liquid or uncured product at the interface between the questionable substrate and the cured gel indicates incompatibility and inhibition of cure.

## USABLE LIFE AND STORAGE

Shelf life is indicated by the "Use Before" date found on the product label. *Dow Corning* two-part products should be stored at or below 25 °C (77 °F). Containers should be kept tightly closed at all times to extend shelf life. Check the product label for specific storage conditions.

## PACKAGING INFORMATION

Multiple packaging sizes are available for this product. Please contact your local distributor or *Dow Corning* representative for information on packaging size and availability.

## HANDLING PRECAUTIONS

**PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND MATERIAL SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE MATERIAL SAFETY DATA SHEET IS AVAILABLE ON THE DOW CORNING WEB SITE AT DOW CORNING.COM, OR FROM YOUR DOW CORNING SALES APPLICATION ENGINEER, OR DISTRIBUTOR, OR BY CALLING DOW CORNING CUSTOMER SERVICE.**

## LIMITATIONS

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

## HEALTH AND ENVIRONMENTAL INFORMATION

To support Customers in their product safety needs, *Dow Corning* has an extensive Product Stewardship organization and a team of Product Safety and Regulatory Compliance (PS&RC) specialists available in each area.

For further information, please see our Web site, [dowcorning.com](http://dowcorning.com) or consult your local *Dow Corning* representative.

**LIMITED WARRANTY  
INFORMATION – PLEASE  
READ CAREFULLY**

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow Corning's sole warranty is that our products will meet the sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

**DOW CORNING SPECIFICALLY  
DISCLAIMS ANY OTHER  
EXPRESS OR IMPLIED  
WARRANTY OF FITNESS FOR A  
PARTICULAR PURPOSE OR  
MERCHANTABILITY.**

**DOW CORNING DISCLAIMS  
LIABILITY FOR ANY  
INCIDENTAL OR  
CONSEQUENTIAL DAMAGES.**

**HOW CAN WE HELP YOU  
TODAY?**

Tell us about your performance, design and manufacturing challenges. Let us put our silicon-based materials expertise, application knowledge and processing experience to work for you.

**For more information** about our materials and capabilities, visit **dowcorning.com**.

To discuss how we could work together to meet your specific needs, email **electronics@dowcorning.com** or go to **dowcorning.com/contactus** for a contact close to your location.

Dow Corning has customer service teams, science and technology centers, application support teams, sales offices and manufacturing sites around the globe.

*We help you invent the future.*™

**dowcorning.com**