

LED Materials

Dow Corning[®] SR-7010

Two part 1:1 mix clear optical grade silicone elastomer

TYPICAL PROPERTIES

Specification Writers: Please contact your local Dow Corning sales office or your Global Dow Corning Connection before writing specifications on this product.

Property	Unit	Value
Viscosity (Part A or Base)	cP	21100
	mPa-sec	21100
	Pa-sec	21.1
Viscosity (Part B or Catalyst)	cP	7275
	mPa-sec	7275
	Pa-sec	7.3
Viscosity (Mixed)	cP	14250
	mPa-sec	14250
	Pa-sec	14.3
NVC (Non Volatile Content)	%	99.7
Working Time at 25°C (Pot Life - hours)	hr	>3
Cure Time @ 170C	minutes	<1
Durometer Shore D	-	70
Refractive Index	-	1.514
Shelf Life at 25°C	months	9
Transmittance @ 380nm, 1.8 mm thick	%	97.3
Transmittance @ 460nm, 1.8mm thick	%	99.2
Transmittance @ 760nm, 1.8mm thick	%	99.9

STORAGE AND SHELF LIFE

Shelf life is indicated by the “Use Before” date found on the product label. Dow Corning two-part products should be stored at or below 25°C (77°F). Containers should be kept tightly closed at all times to extend shelf life. Check the product label for specific storage conditions.

DESCRIPTION

Dow Corning® brand silicone LED (light emitting diode) encapsulants are designed to meet the challenging needs of the LED market, including high adhesion, high purity, moisture resistance, thermal stability and optical transmittance. Silicone materials can absorb stresses caused by thermal cycling inside the package, protecting the chip and the bonding wires. And with the electronics industry quickly moving toward lead-free processing, silicone encapsulants, with their demonstrated, excellent stability at reflow temperatures, are a natural fit for LED applications.

PREPARING SURFACES

Surfaces should be clean and dry. Recommended cleaning methods include Dow Corning® brand OS Fluids, naphtha, mineral spirits, methyl ethyl ketone (MEK) or other suitable solvent. Rougher surfaces tend to promote adhesion of silicones to other surfaces.

PROCESSING/CURING

These products are also compatible with commercially available equipment and industry standard processes. These materials can be dispensed or molded depending on the product and application. Dow Corning OS Fluids are recommended to clean cured or uncured silicone residue from application equipment.

ADHESION

Dow Corning LED materials are specially designed for adhesion to commonly used LED substrates. Surface treatments such as chemical

etching or plasma treatment may provide a reactive surface and improve adhesion to these types of substrates. In general, increasing the cure temperature and/or cure time will improve the ultimate adhesion.

USEFUL TEMPERATURE RANGES

For most uses, silicone encapsulants and resins should be operational over a temperature range of -45 to 200°C (-49 to 392°F) for long periods of time. However, at both the low- and high-temperature ends of the spectrum, behavior of the materials and performance in particular applications can become more complex and require additional considerations. For low-temperature performance, thermal cycling to conditions such as -55°C (-67°F) may be possible, but performance should be verified for your parts or assemblies. Factors that may influence performance are configuration and stress sensitivity of components, cooling rates and hold times, and prior temperature history. At the high-temperature end, the durability of the cured silicone encapsulants and resins is time and temperature dependent. As expected, the higher the temperature, the shorter the time the material will remain useable.

COMPATIBILITY

Certain materials, chemicals, curing agents and plasticizers can inhibit the cure of addition cure adhesives. Most notable of these include: Organotin and other organometallic compounds, Silicone rubber containing organotin catalyst, Sulfur, polysulfides, polysulfones or other sulfur containing materials, unsaturated hydrocarbon plasticizers, and some solder flux residues. If a substrate or material is questionable with respect to potentially causing inhibition of cure, it is recommended that a small scale compatibility test be run to ascertain suitability in a given application. The presence of liquid or uncured product at the interface between the questionable substrate

and the cured gel indicates incompatibility and inhibition of cure.

HEALTH AND ENVIRONMENTAL INFORMATION

To support customers in their product safety needs, Dow Corning has an extensive Product Stewardship organization and a team of Product Safety and Regulatory Compliance (PS&RC) specialists available in each area. For further information, please see our website, www.dowcorning.com, or consult your local Dow Corning representative.

LIMITATIONS

These products are neither tested nor represented as suitable for medical or pharmaceutical uses.

LIMITED WARRANTY INFORMATION PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that Dow Corning's products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent. Dow Corning's sole warranty is that the product will meet the Dow Corning sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. DOW CORNING SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. DOW CORNING DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.

**SAFE HANDLING
INFORMATION**

PRODUCT SAFETY
INFORMATION REQUIRED FOR
SAFE USE IS NOT INCLUDED IN
THIS DOCUMENT. BEFORE
HANDLING, READ PRODUCT
AND MATERIAL SAFETY DATA
SHEETS AND CONTAINER
LABELS FOR SAFE USE,
PHYSICAL AND HEALTH
HAZARD INFORMATION. THE
MATERIAL SAFETY DATA
SHEET IS AVAILABLE ON THE

DOW CORNING WEBSITE AT
WWW.DOWCORNING.COM, OR
FROM YOUR DOW CORNING
REPRESENTATIVE, OR
DISTRIBUTOR, OR BY CALLING
YOUR GLOBAL DOW CORNING
CONNECTION.

For More Information

To learn more about these and other
products available from Dow
Corning, please visit the Dow
Corning Electronics website at
www.dowcorning.com/electronics.



Electronics
Solutions

Dow Corning and Sylgard are registered trademarks of Dow Corning Corporation.
All other trademarks or brand names are the property of their respective owners.
©2008 Dow Corning Corporation. All rights reserved. Printed in USA Form No.
11-1308A-01