



Körapur 666

General Properties	Technology/Base	polyurethane
	Type of Product	adhesive
	Curing	polyaddition curing
	Mechanical Properties	structural
	Parts	two part system
	Part A (Resin)	Körapur 666
	Part B (Hardener)	Köracur TH 650
	Colour	beige
	Product Benefits	improved humidity resistance high mechanical properties flexible use in various applications no significant shrinkage wide range of pot life profiles available



Technical Data

Part A Körapur 666

Physical Properties Density Colour	1.70 g/cm ³ beige	DIN EN 542
Processing Guidelines and Parameters Storage Temperature Viscosity	15 °C to 25 °C 5,000,000 mPa·s	Kö-test method 100000

Part B Köracur TH 650

Physical Properties Density NCO content Colour	1.23 g/cm ³ 31% brown	DIN EN 542
Processing Guidelines and Parameters Storage Temperature Viscosity	10 °C to 25 °C 300 mPa·s	Kö-test method 100000



General

Physical Properties		
Density	1.60 g/cm ³	DIN EN 542
Glass Transition Temperature	50 °C	DIN EN ISO 6721-1
Processing Guidelines and Parameters		
Mixing Ratio (Part A : Part B) by Weight	6.0 : 1	
Mixing Ratio (Part A : Part B) by Volume	4.5 : 1	
Processing Temperature	15 °C to 25 °C	
Viscosity	55,000 mPa·s	Kö-test method 100003, Kö-test method 100003
Curing		
Potlife	90 min, 60 min, 45 min, 30 min, 25 min, 20 min, 18 min, 10 min, 8 min, 5 min, 3 min	Kö-test method 100178
Cured Material Characteristics		
Shore Hardness (Type D)	70	ISO 868 / DIN ISO 7619-1
Tensile Strength	15 MPa	DIN EN ISO 527
Elongation at Break	3%	DIN EN ISO 527
G ₁₀ -Modulus	140 MPa	DIN EN 14869-2
Lap Shear Strength	17 MPa	DIN EN 14869-2, substrates: aluminum/aluminum
Service Conditions		
Service Temperature	-160 °C to 90 °C	
Short-term temperature resistance	120 °C	



Product Properties

Applications	Fields of Application	automotive construction industrial assembly transportation
	Special Applications	side wall, floor and roof assemblies for trailer constructions sandwich assemblies
Processing	Suitable Substrates	polystyrene-rigid foam (EPS) various aluminum alloys various steel alloys polyurethane (PUR) polyvinyl chloride (PVC) various composite materials (e.g. CFRP, GFRP) wood various other substrates
	Consistency	non-sagging pasty
	Surface Requirements	dry clean free of grease free of dust
	Application Method	via two part mixing and metering systems using mixing cartridge
	Product is free of	solvents plasticizers
Cleaning	Cleaner for Tools	Körasolv PU
Certifications	Certifications and Declarations of Conformity	meets the requirements of the International Maritime Organisation (IMO)
Hints	Moisture Sensitivity	The adhesive must not be exposed to moisture before and during application. Moisture causes foaming leading to lower mechanical properties.



Additional Information

Storage

Körapur 666 should be used within the shelf life specified on the packaging. The storage stability only applies to material stored under appropriate conditions (original unopened containers, recommended storage temperature).

Safety

Please read our Safety Data Sheet (SDS) and the labels of each product before use. The valid safety regulations must be considered.

Preparation

For some substrates the use of mechanical pre-treatment and/or cleaner or primer is necessary to achieve good adhesion. Refer to the product properties section of this data sheet for special surface requirements and suitable adhesion promoters.

Processing

Refer to the technical data table regarding processing parameters. Low temperatures can cause a temporary increase in viscosity resulting in reduced extrusion and slower curing rates.

Cleaning

Clean tools immediately after use. Once cured, the material can only be removed mechanically. Appropriate cleaners are listed in the product properties table. For further information please contact your local sales office.

Disposal

Please refer to the Safety Data Sheet (SDS) for appropriate disposal instructions.

IMPORTANT: Information, specifications, procedures and recommendations provided (information) are based on our experience and we believe this to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is users sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. The user is advised to review the specific context of the intended use to determine whether the users intended use violates any law or infringes upon any patent(s). No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

NOTE TO USER: by ordering/receiving product you accept the **H.B. Fuller General Terms and Conditions of Sale** applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, (1) **the total aggregate liability of H.B. Fuller** for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, **is limited to replacement of affected products or refund of the purchase price for affected products.** (2) H.B. Fuller shall not be liable for **loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses** arising out of or in connection with product supply. (3) Nothing in any term shall operate to exclude or limit H.B. Fullers liability for fraud, gross negligence or for death or personal injury caused by negligence, or for breach of any mandatory implied terms unless permitted by law.